

Weich-PVC-Isolierband

Zumbelband

PVC-Insulation-Tape



Beschreibung

Die Sorte 590 besteht aus einer zähen, reißfesten Weich-PVC-Folie, die einseitig mit einem sehr aggressiven, alterungsbeständigen Naturkautschukkleber beschichtet ist. Die Sorte 590 ist wasserdicht, kältefest und beständig gegen Feuchtigkeit, Öle, Laugen, Säuren und vielen anderen Chemikalien. Es hat eine VDE-Zulassung und ist flammhemmend.

Anwendung

Die Sorte 590 wird zum Bündeln, Reparieren und Kennzeichnen von Kabeln und zum Fixieren von Kabeln und anderen Materialien an Traversen, Bühnen etc. eingesetzt.

Product Description

Type 590 consists of a tough and tear proof LD-PVC-foil, on one side coated with an aggressive, ageing resistant natural rubber adhesive. Type 590 is waterproof and resistant to cold, moisture, oils, bases, acids and many other chemicals. It has a VDE-permission and is flame retardant.

Application

Type 590 is used for bundling, repairing and marking of cables as well as for fixing of cables and other materials on trusses, stages, etc.

Technische Daten

Träger	Weich-PVC-Folie
Gesamtdicke	150 µ
Dehnung bis Bruch	150 %
Klebkraft auf Stahl	1,75 N/cm
Zugfestigkeit	17,7 N/cm
Klebstoff	Naturkautschuk
Temperaturbeständigkeit	bis 90° C
Durchschlagsfestigkeit	6000 V
Kerndurchmesser	32 mm
Farbe	blau, braun, gelb, grau, grün, orange, rot, schwarz, weiß, violett
Länge	25 m

Technical Data

Backing	LD-PVC-foil
Total thickness	150 µ
Elongation at break	150 %
Adhesion on steel	1,75 N/cm
Tensile strength	17,7 N/cm
Adhesive	natural rubber
Temperature resistance	up to 90° C
Dielectric strength	6000 V
Core diameter	32 mm
Colour	blue, brown, yellow, green, grey, orange, red, black, white, violet
Length	25 m

Verpackungseinheiten

Bandbreite in mm	Rollen pro Karton
19	120
50 schwarz	48
19 mm x 10 m Regenbogenpack	200 Bänder = 20 Türme

Packaging

Roll width mm	Rolls per carton
19	120
50 black	48
19 mm x 10 m rainbowntower	200 tapes = 20 towers

The information is based on our current knowledge and experience. No guarantee of specific properties or the suitability of the product for a particular purpose can be inferred from our information. All descriptions, drawings, photographs, data, ratios, weights, etc. contained herein are subject to change without notice and do not constitute the contractually agreed quality of the product. Technical changes, dimensional changes, printing errors, and mistakes are reserved.